

BRICK®/BRICK GLOSSY

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	♣ Certifications		
PU	1000 microns	non adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX® COMPIDENCE IN TEXTILES STANDARD 100 15.HIT.75859 HOHENSTEIN HTI		

APPLICATION INSTRUCTIONS

	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
	60°	150 gf	10 cm/sec	25 seconds	155°C (311°F)	Medium/High (2,5/>3,5 bar)	cold

- NOTE: Due to the thickness of the material, we do not recommend cutting details of dimensions less than 0,5 cm
- → Mirror cut the design
- → Weed excess material
- → Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier cold

PRODUCT HIGHLIGHTS

- → Our thickest product
- → Adds dimension to any logo
- NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



