

# **HI-5**

#### **SPECIFICATIONS**

Composition	्रे Average Thickness	Carrier	<b>♣</b> Certifications			
			REACH n° 1907/2006/EU			
PU	90 microns	Adhesive polyester	OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 084270.0 CENTROCOT			

## APPLICATION INSTRUCTIONS

cotton, polyester, poly/cotton blends, performance wear,elastan	SUGGES Blade	TED CUTTING 9	Speed	Time	TRANSFER  Temperature*  Textile Weight*	SETTINGS  Pressure	Peel
	45°	50 gf	25 cm/sec	5 seconds	120°C : ≤ 150g/m² 150°C : > 150g/m²	High (>3,5 bar)	hot/cold

- → Cut the material mirrored
- → Peel off excess material
- → Place the decoration on the garment
- → Apply following the recommended parameters\*
- → Remove the carrier hot or cold

#### **PRODUCT HIGHLIGHTS**

- → Reduced thickness
- → Suitable for technical fabrics
- → Reduced application temperatures
  - NOTE: We highly recommend to perform a test before launching a production

### CARE AND WASHING RECOMMENDATIONS

<b>W</b> Washing	# Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	<b>♦</b> ► Position
Up to 60°C, best inside-out	YES best inside-out	YES (synthetic cycle)	YES	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact ousales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



